

Application No.: 09/934031

Case No.: 56091US002

**In the Claims**

Please amend claims 1, 10, 23, and 31; add new claims 35-37; and cancel claims 9, 14, 29, and 34. Per 37 C.F.R. § 1.121, all currently-amended claims are submitted below with markings to indicate the changes that have been made relative to the immediate prior version of the claims. No separate "clean" version of the currently amended claims is included as this requirement has been eliminated. Further, pending claims not being currently amended that are under examination are presented below in a clean version.

- B1
1. **(Currently Amended)** An article comprising:  
a tape including an adhesive side and a non-adhesive side, wherein the adhesive side is coated with a pressure-sensitive adhesive; and  
a layer of retroreflective beads that are partially embedded in the non-adhesive side of the tape, wherein the layer of retroreflective beads is substantially held in place in the non-adhesive side of the tape without the use of an additional adhesive or a resin.
  2. **(Original)** The article of claim 1, wherein the tape is medical tape capable of being comfortably adhered to human skin.
  3. **(Cancelled)**
  4. **(Original)** The article of claim 1, wherein the tape is medical tape having a foam backing.
  5. **(Original)** The article of claim 1, wherein the tape is medical tape having a non woven backing.
  6. **(Original)** The article of claim 1, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than seventy percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

7. **(Original)** The article claim 1, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

B1  
8. **(Original)** The article claim 1, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is greater than 5000.

9. **(Cancelled)**

10. **(Currently Amended)** An article comprising:  
a foam backing including a first side and a second side; and  
a layer of retroreflective beads that are partially embedded in the first side of the foam backing, wherein the retroreflective beads comprise a coating comprising aluminum.

11. **(Previously presented)** The article of claim 10, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than seventy percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

12. **(Previously presented)** The article of claim 10, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

13. **(Previously presented)** The article of claim 10, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is greater than 5000.

14. **(Cancelled)**

15. **(Original)** A method comprising:

covering a non-adhesive side of a pressure-sensitive adhesive tape with retroreflective beads; and

applying heat and pressure to melt the retroreflective beads into the non-adhesive side of the pressure-sensitive adhesive tape.

16. **(Original)** The method of claim 15, wherein the retroreflective beads comprise glass beads coated with aluminum, wherein each glass bead is coated with aluminum on approximately half of a glass bead surface area.

17. **(Original)** The method of claim 15, wherein the retroreflective beads are fully aluminum coated glass beads, the method further comprising etching aluminum from exposed surfaces of the retroreflective beads.

18. **(Original)** The method of claim 15, wherein applying heat and pressure comprises laminating the retroreflective beads onto the non-adhesive side of the pressure-sensitive adhesive tape.

19. **(Original)** A method comprising:

covering a first side of a foam backing with retroreflective beads; and

applying heat and pressure to melt the retroreflective beads into the first side of the foam backing.

Application No.: 09/934031

Case No.: 56091US002

20. **(Original)** The method of claim 19, wherein the retroreflective beads comprise glass beads coated with aluminum, wherein each glass bead is coated with aluminum on approximately half of a glass bead surface area.

21. **(Original)** The method of claim 19, wherein the retroreflective beads are fully aluminum coated glass beads, the method further comprising etching aluminum from exposed surfaces of the retroreflective beads.

B | 22. **(Original)** The method of claim 19, wherein applying heat and pressure comprises laminating the retroreflective beads into the first side of the foam backing.

23. **(Currently Amended)** An article comprising:  
a foam backing including first and second sides;  
a pressure-sensitive adhesive material covering the first side; and  
a layer of retroreflective beads that are partially embedded in the second side, wherein the retroreflective beads comprise a coating comprising aluminum.

24. **(Previously presented)** The article of claim 23, wherein the article is made by the process of:  
coating the first side of the foam backing with the pressure-sensitive adhesive material;  
covering the second side of the foam backing with retroreflective beads; and  
applying heat and pressure to partially embed the retroreflective beads in the second side of the foam backing.

25. **(Original)** The article of claim 24, wherein applying heat and pressure comprises laminating the retroreflective beads onto the second side of the foam backing.

26. **(Original)** The article of claim 23, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective

Application No.: 09/934031

Case No.: 56091US002

brightness is greater than seventy percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

27. **(Original)** The article of claim 23, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

B | 28. **(Original)** The article of claim 23, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is greater than 5000.

29. **(Cancelled)**

30. **(Original)** The article of claim 23, wherein the foam backing comprises a closed-cell cross-linked foam.

31. **(Currently Amended)** An article comprising:

a medical tape capable of being comfortably adhered to human skin, the medical tape including an adhesive side and a non-adhesive side, wherein the adhesive side is coated with a pressure-sensitive adhesive; and

a layer of retroreflective beads that are partially embedded in the non-adhesive side of the medical tape, wherein the retroreflective beads comprise a coating comprising aluminum, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than seventy percent of the initial reflective brightness when the number of abrasion cycles is approximately 750.

Application No.: 09/934031

Case No.: 56091US002

32. (Original) The article of claim 31, wherein the medical tape includes a foam backing.

33. (Original) The article claim 31, wherein the final reflective brightness is greater than ninety percent of the initial reflective brightness when the number of abrasion cycles is greater than 5000.

34. (Cancelled)

35. (New) An article comprising:

a foam backing including a first side and a second side; and  
a layer of retroreflective beads that are partially embedded in the first side of the foam backing, wherein the layer of retroreflective beads is substantially held in place in the first side of the foam backing without the use of an additional adhesive or a resin.

36. (New) An article comprising:

a foam backing including first and second sides;  
a pressure-sensitive adhesive material covering the first side; and  
a layer of retroreflective beads that are partially embedded in the second side, wherein the layer of retroreflective beads is substantially held in place in the first side of the foam backing without the use of an adhesive or a resin.

37. (New) An article comprising:

a medical tape capable of being comfortably adhered to human skin, the medical tape including an adhesive side and a non-adhesive side, wherein the adhesive side is coated with a pressure-sensitive adhesive; and

a layer of retroreflective beads that are partially embedded in the non-adhesive side of the medical tape, wherein the layer of retroreflective beads exhibits an initial reflective brightness prior to being subjected to abrasion cycles and a final reflective brightness after being subjected to a number of abrasion cycles, wherein the final reflective brightness is greater than seventy percent of the initial reflective brightness when the number of abrasion cycles is approximately

SEP. 9. 2003 4:15PM

3M LEGAL 220 11W

NO. 5521 P. 9

Application N. : 09/934031

Case No.: 56091US002

B1 750, and further wherein the layer of retroreflective beads is substantially held in place on the non-adhesive side of the medical tape without the use of an adhesive or resin.